TABLE 1050-2 PROPERTIES OF FENCING MATERIALS					
Item	Gauge or Diameter, inch	Coating, oz/sf	FENCING Coating, oz/sf, Aluminum	Remarks	
Tie wires, steel	9	0.90	0.40	For fastening chain link fabric and tension wire to tubular sections or to roll formed steel line posts.	
Tie wires, Aluminum	6	-	-	Alloy 1350-H19 or approved equal.	
Clips, steel wire	7	0.90	-	For fastening chain link fabric and tension wire to H- posts.	
Clips, steel wire	11	0.85	-	For fastening woven wire fabric to steel posts.	
Hog rings, steel	12	0.80	0.40	For fastening chain link fabric to tension wire.	
Hog rings, aluminum	9	-	-	Alloy 1350-H19 or approved equal.	
Truss rod, steel	5/16	2.00	-	-	
Tension (stretcher) bars, steel	3/16 x 3/4	1.50	-	For connection of 1 3/4" or 2" fabric to end, gate and corner posts for fabric heights over 5 ft.	
Tension (stretcher) bars, steel	3/16 x 5/8	1.50	-	For connection of 1 3/4" or 2" fabric to end, gate and corner posts for fabric heights up to 5 ft.	
Tension (stretcher) bars, steel	1/4 x 3/8	1.50	-	For connection of 1" fabric to end, gate, and corner posts.	
Staples, Nails or	9	0.35	-	For fastening woven wire to timber posts. Shall be the size and shape shown in the plans.	
Tension wire braces	9	0.90	0.40	For woven wire fence.	
Post and line caps	-	1.30	-	For installation on top of posts to guard against moisture.	
Rail and brace ends (pressed steel or cast iron)	-	1.30	-	-	
Top rail steel sleeves	0.051	1.30	-	For rail connections. shall be fabricated to prevent movement along the rail.	
Tension band	14	1.30	-	For fastening tension bar to posts.	
Brace band	12	1.30	-	For fastening rail to posts.	
Barbed wire extension arms (pressed steel or cast iron)	14	1.30	-	Shall be fitted with clips or slots for attaching the barbed wire to the arms.	
Hinges, latches	_	2.00	_	_	

1

2

SECTION 1052 SALT AND LIME STABILIZERS

3 1052-1 SODIUM CHLORIDE

4 Sodium chloride shall meet AASHTO M 143.

5 1052-2 CALCIUM CHLORIDE

6 Calcium chloride shall be Class S or L meeting AASHTO M 144.

Section 1054

1	1052-3 LIME
2	(A) Chemical Requirements
3 4	Quicklime and hydrated lime for soil stabilization shall meet ASTM C977 except that it shall contain at least 86% available calcium oxide (CaO) on an LOI-free basis.
5	(B) Physical Requirements
6	(1) Hydrated Lime
7	Hydrated lime shall have at least 85% passing a No. 200 sieve.
8	(2) Quicklime
9	Grade quicklime so 100% passes a 1/4" sieve.
10	(C) Sampling and Inspection
11 12 13	Furnish Type 1 or Type 2 material certifications with each shipment of lime attesting that the lime meets the Specifications in accordance with Article 106-3; however, the material will be subject to inspection, test or rejection by the Engineer at any time.
14 15 16	Lime from more than one source or more than one type may be used on the same project, but the different limes shall not be mixed. Protect the lime from exposure until used and sufficiently dry it to flow freely when handled.
17	SECTION 1054
18	DRAINS
19	1054-1 DECK DRAINS
20 21	Provide deck drains made of PVC pipe or of steel pipe. Use the type of pipe as shown in the plans.
22	PVC pipe shall meet ASTM D1785 or D2665, and have four 1/2" square lugs shop glued at

- 22 approximately equal spacing around the pipe at 3" from the top end of each deck drain.
- 24 Steel pipe shall meet ASTM A53 for standard weight galvanized pipe.

25 **1054-2 FUNNELS AND FUNNEL DRAINS**

26 (A) Funnels

- Fabricate funnels for corrugated aluminum alloy pipe from clad aluminum alloy sheets
 meeting AASHTO M 196. Perform fabrication by riveting. The completed funnel shall
 meet AASHTO M 196.
- Fabricate funnels for corrugated steel pipe of steel meeting AASHTO M 218.
 Fabrication may be by riveting or by welding. The completed funnel shall meet
 AASHTO M 36.

33 (B) Funnel Drain Pipe, Elbows and Fittings

Funnel drain pipe, elbows and other fittings may be, at the option of the Contractor, either corrugated aluminum alloy or corrugated steel. Corrugated aluminum alloy pipe, elbows and other fittings shall meet Article 1032-2. Corrugated steel pipe, elbows and other fittings shall meet Article 1032-3.