

Minimum dry film thickness of paint	.013'' (13 mils)
Minimum dry film thickness of Epoxy on concrete	.020'' (20 mils)
Minimum dry film thickness of Epoxy on asphalt	.020'' (20 mils)
Various thicknesses for Alkyd/Maleic Thermoplastic	.090 - .120" (90 - 120 mils)
Minimum dry film thickness of polyurea	.020'' (20 mils)