

# TECHNICIAN'S CHECKLIST

## SECTION 660

### ASPHALT SURFACE TREATMENT

PROJECT: \_\_\_\_\_  
 REVIEW DATE: \_\_\_\_\_

TECHNICIAN: \_\_\_\_\_  
 REVIEWER: \_\_\_\_\_

ACTION	YES	NO	N/A	COMMENTS
Study Specifications, Plans, and Special Provisions				
Refer to the Special Provisions to determine whether a specific grade of asphalt and/or aggregate and application rate are specified. When the grade of asphalt is not specified the Contractor may use any grade of asphalt shown in Table 660-1 for the type of treatment.				
Ensure that the aggregate used is clean.				
Ensure the surface of the base material is dry in order to obtain satisfactory results from the application of the asphalt material.				
Ensure all damaged or defective areas have been repaired prior to the application of asphalt.				
If the asphalt material appears questionable, take a sample.				
Ensure that the asphalt material is being applied uniformly and at the temperature rates specified in Table 660-1.				
Ensure the cover aggregates are spread uniformly, immediately after the asphalt application. The aggregate must be applied before the asphalt begins to "break".				
Ensure a string line has been placed to guide the application equipment unless otherwise permitted.				
Verify during the initial coverage that the aggregate is not being crushed appreciably. If crushing is occurring, use a lighter steel wheel roller.				
Ensure paper has been placed across the surface at all starting points to ensure the distributor is operating at full force when the application begins and ends.				
Ensure the aggregates have been tested and approved prior to their incorporation into the seal coat.				
Ensure that all pay items as defined in the Specifications (Section 660-11) are measured and properly recorded in appropriate pay record books.				