

Mix Types:

1. Type A (Coarsest – 100% Passing $\frac{3}{4}$ "
2. Type B (Mid-Size – 100% Passing $\frac{1}{2}$ "
3. Type C (Finest Size – 100% Passing $\frac{3}{8}$ "

Rates of Application:

1. Mix
 - a. Type A = 90 lbs./yd² (+/- $\frac{3}{4}$ " uncompact)
 - b. Type B = 70 lbs./yd² (+/- $\frac{5}{8}$ " uncompact)
 - c. Type C = 50 lbs./yd² (+/- $\frac{1}{2}$ " uncompact)
2. Polymer-modified emulsion = Typically in range of 0.15 to 0.25 gals/yd² but exact rate will be under "Comments" on JMF.