

Table 2
Tolerances for Comparisons of Fine Aggregate QC/QA Gradations

Sieve Sizes	Asphalt Sand, SD, SW, SSW*	1S	2S	2MS	4S	Super Washed Screenings
HiCAMS Size	AS, SD, SW, SSW	S1S	S2S	S2MS	S4S	SSW
1/2"						
3/8"						
#4	± 2					± 2
#8	± 6	± 1	± 1	± 1	± 2	± 6
#10	± 6					± 6
#16	± 6	± 3	± 3	± 3	± 3	± 6
#30	± 6	± 3	± 3	± 3	± 3	± 6
#40	± 6					± 6
#50	± 4	± 2	± 2	± 2	± 3	± 4
#100	± 2	± 1	± 1	± 1	± 2	± 2
#200	± 2	± 1	± 1	± 1	± 1	± 2

*DS- Dry Screenings, WS-Washed Screenings, SWS- Super Washed Screenings