

Tensor Geogrid

Geogrid and Direction (MD, CD)	Polymer (PET, HDPE, PP)	Aperture Size (inches)	T _{ult} (lb/ft)	T _{2%} (lb/ft)	T _{5%} (lb/ft)	J _{ave} (lb)	J (m-N/deg)	RF _{CR}			RF _D
								3-yr	75-yr	100-yr	
BX1120 (CD)	PP	1.3	1,300	450	920						
Borrow ($\phi = 30^\circ$)											
Geogrid and Direction (MD, CD)	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	ρ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
BX1120(CD)								0.8	0.462	0.8	24.79
Fine Aggregate ($\phi = 34^\circ$)											
Geogrid and Direction (MD, CD)	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	ρ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
BX1120(CD)								0.8	0.54	0.8	28.35
Coarse Aggregate ($\phi = 38^\circ$)											
Geogrid and Direction (MD, CD)	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	ρ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
BX1120 (CD)								0.9	0.7	0.8	32.0

Where,

T_{ult} = wide width tensile strength @ ultimate (lb/ft),

T_{2%} = wide width tensile strength @ 2% strain (lb/ft),

T_{5%} = wide width tensile strength @ 5% strain (lb/ft),

J_{ave} = average junction strength per rib (lb),

J = aperture stability modulus (m-N/deg),

RF_{CR} = creep reduction factor for 3, 75 and 100-yr design life,

RF_D = durability (degradation) reduction factor,

RF_{ID} = installation damage reduction factor,

RF = (RF_{CR} × RF_{ID}) for 3-yr design life or (RF_{CR} × RF_D × RF_{ID}) for 75 and 100-yr design life,

T_{al} = short-term design strength for 3-yr design life or LTDS for 75 and 100-yr design life (lb/ft) = T_{ult} / RF,

C_i = coefficient of interaction,

F* = pullout resistance factor = C_i tan ϕ ,

C_{ds} = coefficient of direct sliding and

tan ρ = soil-geogrid friction angle (deg) = C_{ds} tan ϕ .