

## TenCate Geogrid

Geogrid and Direction (MD, CD)	Polymer (PET, HDPE, PP)	Aperture Size (inches)	T <sub>ult</sub> (lb/ft)	T <sub>2%</sub> (lb/ft)	T <sub>5%</sub> (lb/ft)	J <sub>ave</sub> (lb)	J (m-N/deg)	RF <sub>CR</sub>			RF <sub>D</sub>
								3-yr	75-yr	100-yr	
Miragrid 22XT (MD)	PET	1.4 x 0.6	20,559	3,700	6,700	-	-	1.37	1.45	1.47	1.30
Geogrid and Direction (MD, CD)	<b>Borrow (<math>\phi = 30^\circ</math>)</b>										
	RF <sub>ID</sub>	RF			T <sub>al</sub> (lb/ft)			C <sub>i</sub>	F*	C <sub>ds</sub>	$\rho$ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
Miragrid 22XT (MD)	1.05	1.44	1.98	2.01	14,292	10,387	10,246	0.85	0.49	0.85	26.1
Geogrid and Direction (MD, CD)	<b>Fine Aggregate (<math>\phi = 34^\circ</math>)</b>										
	RF <sub>ID</sub>	RF			T <sub>al</sub> (lb/ft)			C <sub>i</sub>	F*	C <sub>ds</sub>	$\rho$ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
Miragrid 22XT (MD)	1.10	1.51	2.07	2.10	13,642	9,915	9,780	0.90	0.61	0.90	31.3
Geogrid and Direction (MD, CD)	<b>Coarse Aggregate (<math>\phi = 38^\circ</math>)</b>										
	RF <sub>ID</sub>	RF			T <sub>al</sub> (lb/ft)			C <sub>i</sub>	F*	C <sub>ds</sub>	$\rho$ (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
Miragrid 22XT (MD)	1.25	1.71	2.36	2.39	12,005	8,725	8,607	0.90	0.70	0.90	35.1

Where,

- T<sub>ult</sub> = wide width tensile strength @ ultimate (lb/ft),
- T<sub>2%</sub> = wide width tensile strength @ 2% strain (lb/ft),
- T<sub>5%</sub> = wide width tensile strength @ 5% strain (lb/ft),
- J<sub>ave</sub> = average junction strength per rib (lb),
- J = aperture stability modulus (m-N/deg),
- RF<sub>CR</sub> = creep reduction factor for 3, 75 and 100-yr design life,
- RF<sub>D</sub> = durability (degradation) reduction factor,
- RF<sub>ID</sub> = installation damage reduction factor,
- RF = (RF<sub>CR</sub> × RF<sub>ID</sub>) for 3-yr design life or (RF<sub>CR</sub> × RF<sub>D</sub> × RF<sub>ID</sub>) for 75 and 100-yr design life,
- T<sub>al</sub> = short-term design strength for 3-yr design life or LTDS for 75 and 100-yr design life (lb/ft) = T<sub>ult</sub> / RF,
- C<sub>i</sub> = coefficient of interaction,
- F\* = pullout resistance factor = C<sub>i</sub> tan  $\phi$  ,
- C<sub>ds</sub> = coefficient of direct sliding and
- tan  $\rho$  = soil-geogrid friction angle (deg) = C<sub>ds</sub> tan  $\phi$  .