

Synteen Geogrid											
Geogrid and Direction (MD, CD)	Polymer (PET, HDPE, PP)	Aperture Size (inches)	T _{ult} (lb/ft)	T _{2%} (lb/ft)	T _{5%} (lb/ft)	J _{ave} (lb)	J (m-N/deg)	RF _{CR}			RF _D
								3-yr	75-yr	100-yr	
SF20 (MD,CD)	PET	1.00 x 0.79	2025					1.43	1.51	1.51	1.30
Geogrid and Direction (MD, CD)	Borrow ($\phi = 30^\circ$)										
	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	P (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
SF20 (MD,CD)	1.05	1.50	2.06	2.06	1349	982	982	0.67	0.39	0.67	21.15
Geogrid and Direction (MD, CD)	Fine Aggregate ($\phi = 34^\circ$)										
	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	P (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
SF20 (MD,CD)	1.10	1.57	2.16	2.16	1287	938	938	0.67	0.45	0.67	24.32
Geogrid and Direction (MD, CD)	Coarse Aggregate ($\phi = 38^\circ$)										
	RF _{ID}	RF			T _{al} (lb/ft)			C _i	F*	C _{ds}	P (deg)
		3-yr	75-yr	100-yr	3-yr	75-yr	100-yr				
SF20 (MD,CD)	1.73	2.47	3.40	3.40	819	596	596	0.67	0.52	0.67	27.63

Where,

- T_{ult} = wide width tensile strength @ ultimate (lb/ft),
- T_{2%} = wide width tensile strength @ 2% strain (lb/ft),
- T_{5%} = wide width tensile strength @ 5% strain (lb/ft),
- J_{ave} = average junction strength per rib (lb),
- J = aperture stability modulus (m-N/deg),
- RF_{CR} = creep reduction factor for 3, 75 and 100-yr design life,
- RF_D = durability (degradation) reduction factor,
- RF_{ID} = installation damage reduction factor,
- RF = (RF_{CR} × RF_{ID}) for 3-yr design life or (RF_{CR} × RF_D × RF_{ID}) for 75 and 100-yr design life,
- T_{al} = short-term design strength for 3-yr design life or LTDS for 75 and 100-yr design life (lb/ft) = T_{ult} / RF,
- C_i = coefficient of interaction,
- F* = pullout resistance factor = C_i tan ϕ ,
- C_{ds} = coefficient of direct sliding and
- tan P = soil-geogrid friction angle (deg) = C_{ds} tan ϕ .