



STATE OF NORTH CAROLINA  
DEPARTMENT OF TRANSPORTATION


ROY COOPER  
GOVERNOR

J. ERIC BOYETTE  
SECRETARY

DATE: July 18, 2020

TO: Division Engineers

FROM: Todd W. Whittington, PE  
State Materials Engineer

DocuSigned by:  
  
D0149743E0534BA...

SUBJECT: Modifications to Table 1000-1 – Slump Requirements for Concrete

To improve workability, finishing, and concrete consolidation in structures with congested steel designs, the allowable slump for Class AA, A, B, and lightweight concrete has been increased to allow up to 6 inches. The additional slump must be achieved by adding a chemical admixture conforming to Section 1024-3.

As prescribed in Note A of the table, in no case shall the water-cement ratio on the approved concrete mix design be exceeded. Concrete exhibiting segregation and/or excessive bleeding will be rejected. Utilizing an admixture to modify slump does not relinquish the contractor's responsibility to ensure the final product quality and overall configuration meets design specifications. Caution should be taken when placing these modified mixes on steep grades to prevent unintended changes to the set slope.

This change will take effect immediately for all contracts. The Standard Specifications and all associated manuals and references have been modified to reflect these changes. For your information, a copy of the special provision SP10 R01, Table 1000-1, is attached.

If you have any questions, please contact Brian Hunter at 919-329-4030 or [bhunter@ncdot.gov](mailto:bhunter@ncdot.gov).

Attachment

cc: Victor Barbour, PE – CAGC  
Caroline Sutton – CRMCA  
Christopher Peoples, PE  
Lamar Sylvester, PE  
Boyd Tharrington, PE  
Brian Hanks, PE  
Division Construction Engineers  
District Engineers  
Resident Engineers

Area Materials Engineers  
Brian Hunter, PE  
Matt Hilderbran, PE  
Sam Frederick  
Cabell Garbee, PE  
James Sawyer, PE  
Joshua Law  
Benard Chola, PE

**PORTLAND CEMENT CONCRETE PRODUCTION AND DELIVERY:**

(9-15-20)

1000, 1014, 1024

SP10 R01

Revise the 2018 Standard Specifications as follows:

**Page 10-6, Table 1000-1, REQUIREMENTS FOR CONCRETE**, replace with the following:

TABLE 1000-1 REQUIREMENTS FOR CONCRETE											
Class of Concrete	Min. Compressive Strength at 28 days	Maximum Water-Cement Ratio				Consistency Maximum Slump		Cement Content			
		Air-Entrained Concrete		Non-Air-Entrained Concrete		Vibrated	Non-Vibrated	Vibrated		Non-Vibrated	
		Rounded Aggregate	Angular Aggregate	Rounded Aggregate	Angular Aggregate			Min.	Max.	Min.	Max.
		Units	psi					inch	inch	lb/cy	lb/cy
AA	4500	0.381	0.426	---	---	3.5 <sup>A</sup>	---	639	715	---	---
AA Slip Form	4500	0.381	0.426	---	---	1.5	---	639	715	---	---
Drilled Pier	4500	---	---	0.450	0.450	---	5 - 7 dry 7 - 9 wet	---	---	640	800
A	3000	0.488	0.532	0.550	0.594	3.5 <sup>A</sup>	4.0	564	---	602	---
B	2500	0.488	0.567	0.559	0.630	1.5 machine placed 2.5 <sup>A</sup> hand placed	4.0	508	---	545	---
Sand Light-weight	4500	---	0.420	---	---	4.0 <sup>A</sup>	---	715	---	---	---
Latex Modified	3000 (at 7 days)	0.400	0.400	---	---	6.0	---	658	---	---	---
Flowable Fill excavatable	150 max. (at 56 days)	as needed	as needed	as needed	as needed	---	Flowable	---	---	40	100
Flowable Fill non-excavatable	125	as needed	as needed	as needed	as needed	---	Flowable	---	---	100	as needed
Pavement	4500 Design, field 650 flexural, design only	0.559	0.559	---	---	1.5 slip form 3.0 hand placed	---	526	---	---	---
Precast	See Table 1077-1	as needed	as needed	---	---	6.0	as needed	as needed	as needed	as needed	as needed
Prestressed	per contract	See Table 1078-1	See Table 1078-1	---	---	8.0	---	564	as needed	---	---

A. The slump may be increased to 6 inches, provided the increase in slump is achieved by adding a chemical admixture conforming to Section 1024-3. In no case shall the water-cement ratio on the

approved design be exceeded. Concrete exhibiting segregation and/or excessive bleeding will be rejected. Utilizing an Admixture to modify slump does not relinquish the contractor's responsibility to ensure the final product quality and overall configuration meets design specifications. Caution should be taken when placing these modified mixes on steep grades to prevent unintended changes to the set slope.