

**TABLE 1005-1
AGGREGATE GRADATION - COARSE AGGREGATE**

Percentage of Total by Weight Passing													
Std. Size #	2"	1 1/2"	1"	3/4"	1/2"	#4	#8	1/2"	#10	#16	#40	#200	Remarks
4	100	90-100	20-55	0-15	-	-	-	-	-	-	-	0-0.6 ^A	Asphalt Plant Mix
467M	100	95-100	-	35-70	-	0-5	-	-	-	-	-	0-0.6 ^A	Asphalt Plant Mix
5	-	100	90-100	20-55	0-10	-	-	0-10	-	-	-	0-0.6 ^A	AST Mat Coat, Sediment Control Stone
57	-	100	95-100	-	25-60	0-10	0-5	25-60	-	-	-	0-0.6 ^A	AST, Str. Conc., Shoulder Drain, Sediment Control Stone
57M	-	100	95-100	-	25-45	0-10	0-5	25-45	-	-	-	0-0.6 ^A	AST, Portland Cement
6M	-	-	100	90-100	20-55	0-8	-	20-55	-	-	-	-	AST, Concrete Pavement
67	-	-	100	90-100	-	0-10	0-5	-	-	-	-	0-0.6 ^A	AST
78M	-	-	-	100	98-100	20-45	0-15	98-100	-	-	-	0-0.6 ^A	AST, Str. Conc., Drilled Piers, Asphalt Plant Mix
14M	-	-	-	-	-	35-70	5-20	-	-	0-8	-	0-0.6 ^A	Asphalt Plant Mix, AST, Weep Hole Drains, Str. Concrete
9	-	-	-	-	-	85-100	10-40	-	-	0-10	-	0-0.6 ^A	AST
ABC	-	100	75-97	-	55-80	35-55	-	55-80	25-45	-	14-30	4-12 ^B	-
ABC (M)	-	-	-	-	100	5-40	0-20	100	-	0-10	-	0-2.5 ^B	Aggregate Stabilization, Aggregate/Base Course, Asphalt Plant Mix
Light-weight	-	100	75- 100	-	45-79	20- 40	-	45-79	0- 25	-	-	0-12	AST

A. See Subarticle 1005-4(A).

B. See Subarticle 1005-4(B).