

## DIVISION 10 MATERIALS

---

### SECTION 1000

#### PORTLAND CEMENT CONCRETE PRODUCTION AND DELIVERY

##### 1000-1 DESCRIPTION

This section addresses Portland cement concrete to be used for pavement, structures and precast and incidental construction. Produce Portland cement concrete composed of Portland cement, fine and coarse aggregates, water and supplementary cementitious material (optional). Include chemical admixtures as required or needed. Ground granulated blast furnace slag, fly ash or silica fume may be substituted for a portion of the Portland cement. Type IL, IP, IS or IT blended cement may be used instead of Portland cement.

Mixes for all Portland cement concrete shall be designed by a Certified Concrete Mix Design Technician or an Engineer licensed by the State of North Carolina.

When concrete for any one pour is furnished by multiple concrete plants, use the same mix design for all concrete, including sources and quantities of ingredients.

If any major change is made to the mix design, submit a new mix design (with the exception of an approved pozzolan source change).

If any change is made to the mix design, also submit new test results showing the mix design conforms to the criteria. Define a major change to the mix design as:

(A) A source change in coarse aggregate, fine aggregate or cement.

(B) A pozzolan class or type change (e.g. Class F fly ash to Class C fly ash)

(C) A quantitative change in coarse aggregate (applies to an increase or decrease greater than 5%), fine aggregate (applies to an increase or decrease greater than 5%), water (applies to an increase only), cement (applies to a decrease only), or pozzolan (applies to an increase or decrease greater than 5%).

Use materials which do not produce a mottled appearance through rusting or other staining of the finished concrete surface.

##### 1000-2 MATERIALS

Refer to Division 10.

<b>Item</b>	<b>Section</b>
Air Entraining Agent	1024-3
Calcium Nitrite Corrosion Inhibitor	1024-3
Chemical Admixtures	1024-3
Coarse Aggregate	1014-2
Fine Aggregate	1014-1
Fly Ash	1024-5
Ground Granulated Blast Furnace Slag	1024-6
Portland Cement	1024-1
Silica Fume	1024-7
Type IL Blended Cement	1024-1
Type IP Blended Cement	1024-1
Type IS Blended Cement	1024-1
Type IT Blended Cement	1024-1
Water	1024-4

## Section 1000

### 1 1000-3 PORTLAND CEMENT CONCRETE FOR PAVEMENT

#### 2 (A) Composition and Design

3 Submit concrete paving mix design in terms of saturated surface dry weights on Materials  
4 and Tests Form 312U for approval at least 30 days before proposed use. Use a mix that  
5 contains at least 526 lbs. of cement per cubic yard, a maximum water cement ratio of  
6 0.559, an air content in the range of 4.5% to 5.5%, a maximum slump of 1.5 inches, a  
7 minimum flexural strength of 650 psi at 28 days and a minimum compressive strength of  
8 4,500 psi at 28 days.

9 Fly ash may be substituted for cement in the mix design up to 30% at a rate of 1.0 lb. of  
10 fly ash to each pound of cement replaced.

11 The cement content of the mix design may be reduced by no more than 50% and replaced  
12 with blast furnace slag pound for pound.

13 Include in the mix design the source of aggregates, cement, fly ash, slag, water and  
14 admixtures; the gradation and specific gravity of the aggregates; the fineness modulus of  
15 the fine aggregate; and the dry rodded unit weight and size of the coarse aggregate.  
16 Submit test results showing that the mix design conforms to the criteria, including the  
17 1, 3, 7, 14 and 28-day strengths of the average of two 6 inch x 6 inch x 20 inch beams and  
18 the average of two 6 inch x 12 inch cylinders for each age made and tested in accordance  
19 with AASHTO R 39, T22 and T97 from a certified laboratory. Design the mix to produce  
20 an average strength sufficient to indicate that a minimum strength of 650 psi in flexure  
21 and 4,500 psi in compression will be achieved in the field within 28 days.

22 Where concrete with a higher slump for hand methods of placing and finishing is  
23 necessary, submit an adjusted mix design for approval to provide a maximum slump of  
24 3 inches and to maintain the water-cementitious material ratio established by the original  
25 mix design.

#### 26 (B) Air Entrainment

27 Entrain air in the concrete by the use of an approved air entraining agent dispensed with  
28 the mixing water, unless prohibited.

29 Provide an air content of  $5.0\% \pm 1.5\%$  in the freshly mixed concrete. The air content will  
30 be determined in accordance with AASHTO T 121, T152 or T196. At the option of the  
31 Engineer, the air content may be measured by the Chace Indicator, in which case  
32 sufficient tests will be made to establish correlation with the test methods of AASHTO  
33 T 121, T152 or T196. Concrete will not be rejected based on tests from the Chase  
34 Indicator.

#### 35 (C) Slump

36 Provide concrete with a maximum slump of 1.5 inches where placed by a fully  
37 mechanized paving train and no more than 3 inches where placed by hand methods.

38 The sample taken for determination of slump will be obtained immediately after the  
39 concrete has been discharged onto the road.

#### 40 (D) Set Retarding Admixture and Water Reducing Admixture

41 With permission, the Contractor may use an approved set retarding admixture,  
42 an approved water reducing admixture or both to facilitate placing and finishing. Use  
43 a quantity of set retarding admixture or water reducing admixture within the range shown  
44 on the current list of approved admixtures maintained by the Materials and Tests Unit.

**(E) Contractor's Responsibility for Process Control**

Before or at the preconstruction conference, submit a plan detailing the process control and the type and frequency of testing and inspection necessary to produce concrete that meets the Specifications. During all batching and delivery operations assign a Certified Concrete Batch Technician on site whose sole duty is to supervise the production and control of the concrete. This duty includes the following:

- (1) Tests and inspections necessary to maintain the stockpiles of aggregates in an unsegregated and uncontaminated condition.
- (2) Calibration of admixture dispensing systems, weighing systems and water gauges.
- (3) Tests and adjustments of mix proportions for moisture content of aggregates.
- (4) Mixer performance tests before reducing mixing time of central mix plant to less than 90 seconds and at other times when deemed necessary by the Engineer.
- (5) Verifying the actual mixing time of the concrete after all materials are introduced into the mixer at the beginning of paving operations and at least once each month.
- (6) Testing all vibrators.
- (7) Tests necessary to document the slump and air content of the mix produced. Determine air content at least twice each day.
- (8) Tests for depth of the pavement in the plastic state.
- (9) Furnishing data to verify that the approved theoretical cement content has been met at intervals not to exceed 50,000 sy of pavement.
- (10) Signing all plant reports, batch tickets and delivery tickets.

The Department certifies technicians who satisfactorily complete examinations prepared and administered by the Department.

Perform all test procedures in compliance with the appropriate articles of Section 1000.

Tests may be witnessed by the Engineer. Document the results of all tests and inspections and make a copy available to the Engineer upon request. Take prompt action to correct conditions that have resulted in or could result in the submission of materials, products, or completed construction that do not conform to the *Standard Specifications*.

**(F) Contractor Not Relieved of Responsibility for End Result**

The Contractor will not be relieved of his obligation to produce a uniform pavement meeting Specifications by reason of:

- (1) The acceptance or approval by the Engineer of the concrete mix design or any adjustments;
- (2) Compliance with the concrete mix design and compliance with the testing requirements and other process control requirements by the Contractor; or
- (3) The failure of the Engineer to perform any tests in the process control, nor the performance of any tests in the process control that indicate compliance with the Specifications.

**Section 1000**

**1000-4 PORTLAND CEMENT CONCRETE FOR STRUCTURES AND INCIDENTAL CONSTRUCTION**

**(A) Composition and Design**

Provide the class of concrete required by the contract.

Submit proposed concrete mix designs for each class of concrete to be used in the work. Mix proportions shall be determined by a testing laboratory approved by the Department. Base mix designs on laboratory trial batches that meet Table 1000-1 and this section.

Submit mix designs in terms of saturated surface dry weights on Materials and Tests Form 312U at least 35 days before proposed use. Adjust batch proportions to compensate for surface moisture contained in the aggregates at the time of batching. Changes in the saturated surface dry mix proportions will not be permitted unless revised mix designs have been submitted to the Engineer and approved.

Accompany Materials and Tests Form 312U with a listing of laboratory test results of aggregate gradation, air content, slump and compressive strength from a certified laboratory. List the compressive strength of at least three 6 inch x 12 inch or 4 inch x 8 inch cylinders at the age of 7 and 28 days.

Perform laboratory tests in accordance with the following test procedures:

Property	Test Method
Aggregate Gradation	AASHTO T 27
Air Content	AASHTO T 152
Slump	AASHTO T 119
Compressive Strength	AASHTO T 22 and T23

The Engineer will review the mix design for compliance with the Specifications and notify the Contractor as to its acceptability. Do not use a mix until written notice has been received. Acceptance of the mix design does not relieve the Contractor of his responsibility to furnish a product that meets the contract. Upon written request from the Contractor, a mix design accepted and used satisfactorily on any Department project may be accepted for use on other projects.

**(B) Air Entrainment**

Entrain air in the concrete unless otherwise indicated in the plans or in the Specifications. Add an air entraining agent at the time of mixing to produce an air content in the freshly mixed concrete of 6.0% ± 1.5% when tested at the job site. Determine the air content in accordance with AASHTO T 121, T152 or T196. Measurement of air content may also be performed by the Chace Indicator, in which case sufficient tests will be made in accordance with AASHTO T 121, T152 or T196 to establish correlation with the Chace Indicator. Concrete for structures will not be rejected based on tests made with the Chase Indicator. Concrete for incidental construction may be rejected based on an average of 3 or more tests made with the Chase Indicator.

Air entraining agent may be added at the job site when permitted by the Engineer.

**(C) Strength of Concrete**

The compressive strength of the concrete will be considered the average compressive strength test results of two 6 inch x 12 inch cylinders, or two 4 inch x 8 inch cylinders if the aggregate size is not larger than size 57 or 57M. Make cylinders in accordance with AASHTO T 23 from the concrete delivered to the work. Make cylinders at such frequencies as the Engineer may determine and cure them in accordance with AASHTO T 23 as modified by the Department. Copies of these modified test procedures are available upon request from the Materials and Tests Unit.



1           When the average compressive strength of the concrete test cylinders is less than the  
2           minimum strength specified in Table 1000-1 and the Engineer determines it is within  
3           reasonable close conformity with strength requirements, concrete strength will be  
4           considered acceptable. When the Engineer determines average cylinder strength is below  
5           the specification, the in-place concrete will be tested. Based on these test results, the  
6           concrete will either be accepted with no reduction in payment or accepted at a reduced  
7           unit price or rejected as set forth in Article 105-3.

8           **(D) Temperature Requirements**

9           The concrete temperature at the time of placement shall be not less than 50°F nor more  
10          than 95°F except where other temperatures are required by Articles 420-4, 420-7, 420-14  
11          and 420-15.

12          Do not place concrete without permission when the air temperature measured at the  
13          location of the concrete operation in the shade away from artificial heat is below 35°F.

14          When such permission is granted, uniformly heat the aggregates and/or water to  
15          a temperature not higher than 150°F. Heated concrete shall be between 55°F and 80°F at  
16          the time of placement.

Section 1000

**TABLE 1000-1  
REQUIREMENTS FOR CONCRETE**

Class of Concrete	Min. Comp. Strength at 28 days	Maximum Water-Cement Ratio				Consistency Max. Slump		Cement Content			
		Air-Entrained Concrete		Non Air-Entrained Concrete		Vibrated	Non-Vibrated	Vibrated		Non-Vibrated	
		Rounded Aggregate	Angular Aggregate	Rounded Aggregate	Angular Aggregate			Min.	Max.	Min.	Max.
<i>Units</i>	<i>psi</i>					<i>inch</i>	<i>inch</i>	<i>lb/cy</i>	<i>lb/cy</i>	<i>lb/cy</i>	<i>lb/cy</i>
AA	4,500	0.381	0.426	-	-	3.5	-	639	715	-	-
AA Slip Form	4,500	0.381	0.426	-	-	1.5	-	639	715	-	-
Drilled Pier	4,500	-	-	0.450	0.450	-	5-7 dry 7-9 wet	-	-	640	800
A	3,000	0.488	0.532	0.550	0.594	3.5	4	564	-	602	-
B	2,500	0.488	0.567	0.559	0.630	1.5 machine placed 2.5 hand place	4	508	-	545	-
Sand Light-weight	4,500	-	0.420	-	-	4	-	715	-	-	-
Latex Modified	3,000 7 day	0.400	0.400	-	-	6	-	658	-	-	-
Flowable Fill excavatable	150 max. at 56 days	as needed	as needed	as needed	as needed	-	Flow-able	-	-	40	100
Flowable Fill non-excavatable	125	as needed	as needed	as needed	as needed	-	Flow-able	-	-	100	as needed
Pavement	4,500 design, field 650 flexural, design only	0.559	0.559	-	-	1.5 slip form 3.0 hand place	-	526	-	-	-
Precast	See Table 1077-1	as needed	as needed	-	-	6	as needed	as needed	as needed	as needed	as needed
Prestress	per contract	See Table 1078-1	See Table 1078-1	-	-	8	-	564	as needed	-	-

1 **(E) Elapsed Time for Placing Concrete**

2 Regulate the delivery so the maximum interval between the placing of batches at the  
3 work site does not exceed 20 minutes. Place concrete before exceeding the times in  
4 Table 1000-2. Measure the elapsed time as the time between adding the mixing water to  
5 the mix and placing the concrete.

**TABLE 1000-2  
ELAPSED TIME FOR PLACING CONCRETE**

Air or Concrete Temperature Whichever is Higher	Maximum Elapsed Time	
	No Retarding Admixture Used	Retarding Admixture Used
90°F or above	30 minutes	1 hr. 15 minutes
80°F through 89°F	45 minutes	1 hr. 30 minutes
79°F or below <sup>A</sup>	60 minutes	1 hr. 45 minutes
70°F through 79°F <sup>B</sup>	60 minutes	1 hr. 45 minutes
69°F or below <sup>B</sup>	1 hr. 30 minutes	2 hr. 15 minutes

1        **A.** Applicable to Class AA, A and Drilled Pier concrete.

2        **B.** Applicable to Class B concrete.

3        **(F) Use of Set Retarding Admixtures**

4        Use an approved set retarding admixture in all concrete placed in the superstructure of  
5        bridges such that the concrete will remain workable until the entire operation of placing  
6        and finishing, including corrective measures, if necessary, has been completed. The  
7        Engineer may waive the use of set retarding admixture when conditions clearly indicate  
8        that it is not needed.

9        Other structural concrete may contain an approved set retarding admixture when  
10       permitted by the Engineer.

11       Use a quantity of set retarding admixture within the range shown on the current list of  
12       approved admixtures issued by the Materials and Tests Unit.

13       **(G) Use of Water Reducing Admixtures**

14       By permission of the Engineer, the Contractor may use an approved water reducing  
15       admixture to facilitate placing and finishing.

16       Use a quantity of water reducing admixture within the range shown on the current list of  
17       approved admixtures issued by the Materials and Tests Unit.

18       **(H) Use of Calcium Chloride**

19       Calcium chloride may be used as a set accelerating agent where permitted by the  
20       Engineer. Use one lb. of calcium chloride per 100 lbs. of cement except where lesser  
21       amounts are directed. Do not use calcium chloride where steel reinforcement, metal  
22       conduit or other metals will be in contact with the concrete. Do not use calcium chloride  
23       in concrete that has a temperature higher than 70°F, or when the air temperature is greater  
24       than 70°F. Provide cold weather protection for concrete containing calcium chloride in  
25       the same manner as is provided for concrete without calcium chloride.

26       Use calcium chloride in liquid form. Use a solution of one lb. or less of calcium chloride  
27       per one quart of water and mix well. To avoid incompatibility with other additives, add  
28       the calcium chloride to the batch after all other ingredients have been put into the mixer.

29       **(I) Use of Fly Ash**

30       Fly ash may be substituted for cement in the mix design up to 30% at a rate of 1.0 lb. of  
31       fly ash to each pound of cement replaced. Use Table 1000-1 to determine the maximum  
32       allowable water-cementitious material (cement + fly ash) ratio for the classes of concrete  
33       listed.

34       **(J) Use of Ground Granulated Blast Furnace Slag**

35       For mixes that contain cement and ground granulated blast furnace slag, the  
36       water-cementitious ratio (cement and slag) shall not exceed the water-cement ratio shown  
37       in Table 1000-1.

## Section 1000

### 1 (K) Use of Calcium Nitrite Corrosion Inhibitor

2 Units with calcium nitrite in a quantity less than specified are subject to rejection.  
3 Furnish concrete powder drilled from representative cylinders to the Engineer, in a  
4 quantity to be specified, to verify the concentrations of calcium nitrite in hardened  
5 concrete. Concrete that fails to contain calcium nitrite at the required concentrations as  
6 tested is subject to rejection. Use air-entraining, water-reducing and/or set-controlling  
7 admixtures compatible with calcium nitrite solutions. Strictly adhere to the  
8 manufacturer's written recommendations regarding the use of admixtures, including  
9 storage, transportation and method of mixing. If preferred, use calcium nitrite, which  
10 acts as an accelerator, in conjunction with a retarder to control the set of concrete, as per  
11 the manufacturer's recommendation. Add an approved calcium nitrite corrosion inhibitor  
12 (30% solids) to the concrete mix at the batch plant for the bridge elements identified by  
13 the plan notes. Use the inhibitor at a minimum rate of 3.0 gal/cy. Ensure that the  
14 hardened concrete contains at least 5.8 lbs/cy nitrite (NO<sub>2</sub>) when tested in accordance  
15 with Materials and Tests Method Chem. C-20.0. The preceding paragraph does not apply  
16 to concrete used in prestressed concrete members. Concrete used in prestressed concrete  
17 members shall be tested in accordance with Subarticle 1078-4(G).

### 18 1000-5 HIGH EARLY STRENGTH PORTLAND CEMENT CONCRETE

19 Use high early strength Portland cement concrete when required by contract. When not  
20 required, it may be used at the Contractor's option with approval of the Engineer.

21 For all classes of concrete, high early strength concrete may be produced by using  
22 Type III Portland cement. To produce high early strength concrete with regular cement, use  
23 a higher class of concrete as follows:

24 For Class A and Class B, use Class AA with a cement content of at least 677 lbs/cy. Other  
25 classes that lend themselves to high early strength with regular cement will be reviewed by  
26 the Engineer on a case-by-case basis.

### 27 1000-6 FLOWABLE FILL

28 Flowable fill consists of Portland cement, water, supplementary cementitious materials and/or  
29 fine aggregate and, optionally, concrete admixtures.

30 Submit the proposed mix design on Materials and Tests Form 312U at least 35 days before  
31 use. Use a testing laboratory approved by the Department to determine mix proportions based  
32 on laboratory trial batches meeting Table 1000-1.

33 State on Form 312U the intended use of the material (excavatable or non-excavatable).  
34 Accompany Form 312U with a listing of compressive strength of at least three 4 inch x 8 inch  
35 cylinders at the age of 28 or 56 days, depending on whether the mix is to be excavated or not.  
36 Air cure the cylinders during the entire period before testing. The Engineer will advise the  
37 Contractor in writing of the acceptability of the mix design.

### 38 1000-7 LATEX MODIFIED CONCRETE

#### 39 (A) Materials

40 Refer to Division 10.

Item	Section
Coarse Aggregate, standard size No. 78M	1014-2
Fine Aggregate	1014-1
Portland Cement	1024-1
Type IL Blended Cement	1024-1
Type IP Blended Cement	1024-1
Type IS Blended Cement	1024-1
Type IT Blended Cement	1024-1
Water	1024-4

- 1 Do not use Type III high early strength cement.
- 2 Use a formulated latex admixture that is a non-hazardous, film forming and polymeric  
3 emulsion in water and is homogeneous and uniform in composition. Add all stabilizers at  
4 the point of manufacture.
- 5 Use a latex modifier conforming to Table 1000-3.

Property	Requirement
Polymer Type	Styrene Butadiene: 68 ± 4% Styrene 32 ± 4% Butadiene
Average Polymer Particle Size	1500 to 2500 Angstroms
Emulsion Stabilizers	Anionic and non-ionic surfactants
Percent Solids	46.5% to 49.0%
Weight per gallon at 75°F	8.40 to 8.60 lb
pH	9.5 to 11.0
Shelf Life	2 Years
Color	White

- 6 Provide a Type 5 material certification for each load of latex emulsion admixture in  
7 accordance with Article 106-3. Test admixture samples to verify compliance with the  
8 requirements before use. Allow 7 days for sampling and testing after delivery to the  
9 project.
- 10 Do not allow the temperature of latex emulsion admixture to fall below 35°F at any time  
11 or exceed 85°F after delivery to the project.
- 12 For latex emulsion that has been in storage, use a transfer pump and lines to recirculate it  
13 before using and sampling.
- 14 For latex modified concrete, use a workable mixture that meets Table 1000-4.
- 15 Measure the slump 4 to 5 minutes after discharge from the mixer.
- 16 Submit the latex modified concrete mix design, completed by the latex emulsion  
17 manufacturer, to the Engineer for review.

Property	Requirement
Cement Content, lb/cy	658 min.
Latex Emulsion Admixture, gal/cy	24.5 min.
Air Content of Plastic Mix, %	3.5 - 6.5
Slump, inches	3 - 6
% Fine Aggregate as percent of total aggregate by weight	50 - 55
7 day Compressive Strength, psi	3,000 min.
Water-Cement Ratio by weight	0.40 max.

18 **(B) Equipment**

- 19 Before beginning any work, obtain approval for all equipment to be used for deck  
20 preparation, mixing, placing, finishing and curing the latex modified concrete.
- 21 Use sandblasting equipment capable of removing all clay, salt deposits, oil and grease  
22 deposits and all other foreign matter. Provide traps or separators to remove oil and water  
23 from the compressed air. Use traps or separators of adequate size and drain them

## Section 1000

1 periodically during operations. For proportioning and mixing, use self-contained, mobile  
2 and continuously mixing equipment that meets the following requirements:

- 3 (1) Use a self-propelled mixer that is capable of carrying sufficient unmixed dry, bulk  
4 cement, sand, coarse aggregate, latex modifier and water to produce at least 6 cy of  
5 concrete on site.
- 6 (2) Use a mixer that is capable of positive measurement of cement introduced into the  
7 mix. Use a recording meter that is visible at all times and equipped with a ticket  
8 printout to indicate the quantity of cement.
- 9 (3) Calibrate the mixers to accurately proportion the specified mix. Before placing latex  
10 modified concrete, perform calibration and yield tests under the Engineer's  
11 supervision in accordance with the Department's written instructions. Copies of  
12 these written instructions are available from the Materials and Tests Unit. Perform  
13 the calibration and yield tests using the material to be used on the project.  
14 Recalibrate the mixer after any major maintenance operation on the mixer, anytime  
15 the source of materials changes or as directed. Furnish all materials and equipment  
16 necessary to perform the calibrations and yield tests.
- 17 (4) Use a mixer that controls the flow of water and latex emulsion into the mix.  
18 Measure the flow rate of water and the latex emulsion with a calibrated flowmeter  
19 coordinated with both the cement and aggregate feeding mechanisms and the mixer.  
20 Adjust the flow rate, as necessary, to control the slump and ensure that the water-  
21 cement ratios are met. In addition to flowmeters, use mixers with accumulative  
22 water and latex meters capable of indicating the number of gallons, to the nearest  
23 0.1 gallon, introduced into the mixer. Filter water and latex with a suitable mesh  
24 filter before it flows through the accumulative water and latex meters.
- 25 (5) Calibrate the mixer to automatically proportion and blend all components of the  
26 indicated composition on a continuous or intermittent basis as the finishing operation  
27 requires. Provide a mixer that discharges mixed material through a conventional  
28 chute and is capable of spraying water over the placement width as it moves ahead to  
29 ensure that the surface to be overlaid is wet before receiving the modified material.
- 30 (6) Mount a tachometer on the unit to indicate the drive shaft speed.
- 31 (7) Use adequate hand tools for placing and leveling concrete down to approximately the  
32 correct level for striking off with the screed.
- 33 (8) Use a finishing machine that meets the approval of the Engineer and the  
34 requirements of the contract. Use a self-propelled finishing machine capable of  
35 forward and reverse movement under positive control. Use a machine with at least 2  
36 finishing devices, one that is a vibrating screed and the other either a vibrating  
37 screed, oscillating screed, or one or more rotating cylindrical drums 48 inches long  
38 or less and operating between 1,500 and 2,500 vpm. Make certain the finishing  
39 machine can finish the surface to within 1 foot of the edges of the area being placed.  
40 Raise all screeds when the finishing machine is moving backwards over the screeded  
41 surface.
- 42 (9) Use screeds with a vibration frequency that is variable between 3,000 and 6,000 vpm  
43 with positive controls. Use screeds with a metal covered bottom face not less than  
44 4 inches wide. Provide screeds with positive control of the vertical position.
- 45 (10) Use supporting rails for travelling of the finishing machine rigid enough to eliminate  
46 deflection from the weight of the machine.

**(C) Proportioning and Mixing of Modified Compositions**

Use mobile continuous mixers that accurately proportion all materials for the specified mixture. Operate the proportioning equipment at the manufacturer's recommended speed verified with the tachometer during calibration and normal operations.

Yield checks and other checks are permitted.

**(D) Contractor's Responsibility for Process Control**

Before or at the preconstruction conference, submit a plan detailing the process control and the type and frequency of testing and inspection necessary to produce concrete that meets the Specifications. During all batching and delivery operations assign a Certified Concrete Batch Technician on site whose sole duty is to supervise the production and control of the concrete. This duty includes the following:

(1) Tests and inspections necessary to maintain the stockpiles of aggregates in an unsegregated and uncontaminated condition.

(2) Calibration of admixture dispensing systems, weighing systems and water gauges.

(3) Tests and adjustments of mix proportions for moisture content of aggregates.

(4) Mixer performance tests before reducing mixing time of central mix plant to less than 90 seconds and at other times when deemed necessary by the Engineer.

(5) Verifying the actual mixing time of the concrete after all materials are introduced into the mixer at the beginning of paving operations and at least once each month.

(6) Testing all vibrators.

(7) Tests necessary to document the slump and air content of the mix produced. Determine air content at least twice each day.

(8) Tests for depth of the pavement in the plastic state.

(9) Furnishing data to verify that the approved theoretical cement content has been met at intervals not to exceed 50,000 sy of pavement.

(10) Signing all plant reports, batch tickets and delivery tickets.

The Department certifies technicians who satisfactorily complete examinations prepared and administered by the Division of Highways.

Perform all test procedures in compliance with the appropriate articles of Section 1000.

Tests may be witnessed by the Engineer. Document the results of all tests and inspections and make a copy available to the Engineer upon request. Take prompt action to correct conditions that have resulted in or could result in the submission of materials, products, or completed construction that do not conform to these specifications.

**1000-8 MEASURING MATERIALS****(A) Weighing Cement**

Measure cement by weight on scales separate from those used for other materials and in a hopper that is entirely free and independent of the hoppers used for weighing the aggregates. When the quantity of cement in a batch exceeds 30% of the full capacity of the scale, ensure the quantity of cement as indicated by the scale is within  $\pm 1\%$  of the required weight. For smaller batches, ensure the quantity of cement as indicated by the scale be not less than the required amount or more than 4% in excess. Equip all beam type scales with a tare beam.

## Section 1000

### 1 (B) Weighing Aggregates

2 Measure aggregates by weight. Base batch weights on saturated surface dry materials  
3 which is the required weight plus the total weight of surface moisture contained in the  
4 aggregate. Ensure the individual aggregates, as weighed, are within  $\pm 2\%$  of the required  
5 weights.

### 6 (C) Water

7 Measure water by volume or by weight. Ensure the quantity of water measured is  
8 within  $\pm 1\%$  of the required amount.

### 9 (D) Admixture Dispensing Systems

10 Provide a separate dispensing system with separate fill and discharge lines for each type  
11 of admixture to be used, except that admixtures may be measured and introduced into the  
12 mix manually if approval has been obtained. Ensure each system is capable of  
13 measuring, displaying and discharging the required amount of admixture into the mix.  
14 Keep dispensing systems clean and in good operating condition. Use a dispensing system  
15 that is either:

16 (1) Manually operated, self-contained; or

17 (2) Semi-automatic or automatic, self-contained; or

18 (3) Interfaced to operate automatically with the concrete batching control panel.

19 Have the admixture dispenser dispense the required quantity of admixture for each  
20 concrete batch within an accuracy of  $\pm 3\%$ . Check the accuracy of the dispenser as  
21 provided below. Check the accuracy at the point of discharge, or through a bypass valve  
22 suitable for obtaining a calibrated sample of admixture and at the volumes normally used  
23 for one half mixer capacity and for full mixer capacity. Determine the accuracy at the  
24 time of installation and check daily during the early part of each day's operation.

25 Include in each system a graduated measuring unit into which the admixture is batched to  
26 permit a quick visual check of accuracy before its discharge. Ensure the measuring unit  
27 is clearly graduated and be of sufficient size to hold the maximum anticipated dose for  
28 one batch. Clearly mark the measuring unit for the type of admixture to be used.

29 Control the discharge sequence so an admixture will not be brought into contact with raw  
30 cement or another admixture before being diluted through contact with the mixing water  
31 in the mixer. Where 2 types of admixtures are being used, do not discharge them into the  
32 mix simultaneously. Add the air entraining agent with the first addition of water and add  
33 any other chemical admixture with the final addition of water, unless otherwise  
34 permitted.

35 Construct the discharge lines to completely empty after each cycle. Locate the admixture  
36 dispensing systems so the batching plant operator will have a visual verification of the  
37 actual quantity of admixture batched.

38 Use air entraining admixtures in accordance with the manufacturer's recommendations  
39 and in such quantity to provide the specified air content in freshly mixed concrete. Use  
40 a quantity of set retarding admixture and of water reducing admixture per 100 lbs. of  
41 cement that is within the range recommended on the current list of approved admixtures  
42 issued by the Materials and Tests Unit.

## 43 1000-9 BATCHING PLANT

### 44 (A) General

45 Plants located on the Department rights of way shall conform to Article 107-3.

46 Have ready mixed concrete plants inspected and approved by the Department before they  
47 are used to produce concrete, either paving, structural or incidental, for the project.



1 Plants shall meet all the applicable requirements of these *Standard Specifications*, and in  
2 addition, ensure each ready mix plant provides at least three acceptable truck mixers or  
3 truck agitators available for use. Use trucks that have an identifying number. Plants  
4 approved by the Department will be placed on a list of approved plants available to the  
5 Contractor. All plants will be subject to reinspection at intervals selected by the  
6 Engineer. Reapproval after each inspection will be contingent on continuing compliance  
7 with the *Standard Specifications*.

#### 8 **(B) Bins and Hoppers**

9 Provide bins with separate compartments for fine aggregates and for each required size of  
10 coarse aggregate in the batching plant. Design each compartment to discharge efficiently  
11 and freely into the weighing hopper. Provide control so, as the quantity desired is being  
12 approached, the material may be added slowly and shut off with precision. Construct  
13 weighing hoppers to eliminate accumulation of tare materials and to discharge fully  
14 unless otherwise permitted. Provide a port or other opening for removing an overload of  
15 any one of the several materials from the hopper.

#### 16 **(C) Scales**

17 Use either the beam type, load cell type or the springless dial type scales for weighing  
18 aggregates and cement. Ensure the minimum graduation on beam or dial is not more than  
19 0.1% of the total capacity of the scale. Methods of weighing, other than beam or  
20 springless dial scales, may be approved by the Engineer provided they meet the required  
21 weighing tolerances. Ensure the scales are accurate within 0.5% under operating  
22 conditions. Make available ten 50 lb. test weights at the plant for checking accuracy.  
23 Use test weights which meet the U.S. Bureau of Standards requirements for calibrating  
24 and testing equipment. Keep all exposed fulcrums, clevises and similar working parts of  
25 scales clean. When beam type scales are used, make provisions for indicating to the  
26 operator that the required load in the weighing hopper is being approached. Ensure the  
27 device indicates at least the last 50 lbs. of load and design it to give a positive indication  
28 of overload of the scales. During charging of the hopper, have all indicating devices in  
29 full view of the operator and provide convenient access to all controls. Ensure the  
30 indicating devices are in the immediate vicinity of the operator and easily readable by the  
31 operator.

#### 32 **(D) Water Measuring Devices**

33 Use devices for measurement of the water which are readily adjustable and are capable of  
34 being set to deliver the required amount and cut off the flow automatically when this  
35 amount has been discharged. Under all operating conditions the device shall have  
36 accuracy within 1% of the quantity of water required for the batch. Arrange the device so  
37 variable pressures in the water supply line will not affect the measurements. Use  
38 measuring tanks of adequate capacity to furnish the maximum mixing water required and  
39 equip them with outside taps and valves to provide for checking their calibration unless  
40 other means are provided for readily and accurately determining the amounts in the tank.

### 41 **1000-10 MIXERS AND AGITATORS**

#### 42 **(A) General**

43 Mixers are defined as equipment to mix concrete and may be stationary or truck  
44 mounted. Agitators are defined as equipment used to haul central mixed concrete and  
45 may be truck mixers or truck agitators. Provide a metal plate or plates attached to each  
46 mixer and agitator in a prominent place on which the manufacturer has plainly marked  
47 the mixing speed of the drum or paddles and the maximum capacity of the drum or  
48 container in terms of volume of mixed concrete. On truck mixers and agitators, show the  
49 manufacturer's recommended agitating and mixing speed of rotation of the mixing drum  
50 or blades. Equip stationary mixers with an acceptable timing device that will not permit  
51 the batch to be discharged until the specified mixing time has elapsed. Equip truck

## Section 1000

1 mixers with counters to verify the number of revolutions of the drum or blades. Actuate  
2 the counters at the initial time the drums have reached mixing speed.

3 Examine mixers and agitators periodically for changes in condition due to accumulation  
4 of hard concrete or mortar, wear of blades or any other condition which decreases mixing  
5 efficiency. Mixers are unacceptable when the radial height or other dimension of the  
6 blade has worn below 90% of the original dimension. This radial height excludes any  
7 lips on the blade and is the height of the blade running perpendicular to the shell of the  
8 drum. Where such conditions are found, do not use the units until they are corrected.

9 Also examine mixers and agitators periodically for general mechanical condition,  
10 including water measuring and discharge apparatus, identifying number on trucks,  
11 condition of the blades, speed of rotation of the drum and condition of the drum.

### 12 (B) Mixer Capacity

13 Do not load truck mixers with concrete with more than 63% of the gross volume of the  
14 drum. Use mixers capable of combining the ingredients of the concrete into a thoroughly  
15 mixed and uniform mass and of discharging the concrete with a satisfactory degree of  
16 uniformity. Use stationary mixers, when loaded at the manufacturers guaranteed mixing  
17 capacity and the concrete mixed for the prescribed mixing time, capable of combining the  
18 ingredients of the concrete into a thoroughly mixed and uniform mass and discharging  
19 the concrete with satisfactory uniformity.

20 Use at least 20% of the rated mixing capacity as the minimum quantity of concrete  
21 permitted to be mixed or agitated in any mixer.

### 22 (C) Agitator Capacity

23 Load the agitator to not exceed 80% of the gross drum volume and have it be capable of  
24 maintaining the concrete in a thoroughly mixed and uniform mass and of discharging the  
25 concrete with a satisfactory degree of uniformity.

### 26 (D) Consistency Tests

27 The Engineer may, from time to time, make slump tests to measure consistency of the  
28 concrete. Take individual samples at approximately the 1/5th point, the midpoint and the  
29 4/5th point of the load, using AASHTO T 119. Such tests will be made within  
30 20 minutes of discharge of that portion of the load. If the results vary by more than 1  
31 inch in slump, do not use the mixer or agitator unless the condition is corrected.

## 32 1000-11 MIXING AND DELIVERY

### 33 (A) General

34 Mix and deliver concrete to the site of the work by one of the following methods, except  
35 where other methods are approved. Maintain responsibility for controlling the materials  
36 and operations as to produce uniform concrete meeting Specifications requirements.

37 When concrete is being produced for structures and incidental construction in accordance  
38 with Article 1000-4, have present during all batching operations a Certified Concrete  
39 Batch Technician employed by the Contractor or concrete supplier. During batching and  
40 delivery, the sole duty of this employee is to supervise the production and control of the  
41 concrete. Perform moisture tests, adjust mix proportions of aggregates for free moisture,  
42 complete and sign Batch Tickets (Materials and Tests Form 903) or approved delivery  
43 tickets and assure quality control of the batching. Delivery tickets will be permitted  
44 instead of batch tickets (Materials and Tests Form 903) provided they have been  
45 reviewed and approved by the Materials and Tests Unit. The Department certifies  
46 technicians who satisfactorily complete examinations prepared and administered by the  
47 Department.

## 1 (1) Central Mixed Concrete

2 Concrete that is mixed completely in a stationary mixer and the mixed concrete  
3 transported to the point of delivery in a truck agitator or in a truck mixer operating at  
4 agitating speed or in non-agitating equipment approved by the Engineer. Perform  
5 mixing within the capacity and at the mixing speeds recommended by the  
6 manufacturer.

## 7 (2) Transit Mixed Concrete

8 Concrete that is mixed completely in a truck mixer while at the batching plant, in  
9 transit, or at the work site.

## 10 (3) Shrink Mixed Concrete

11 Concrete that is mixed partially in a stationary mixer at a central mixing plant and  
12 completed as transit mixed concrete. Place all ingredients for a batch in the  
13 stationary mixer, partially mix before any concrete is discharged to the truck mixer  
14 and do not exceed the rated capacity of the equipment for the batch size. The mixing  
15 time at the stationary mixer may be reduced to the minimum necessary to  
16 intermingle the ingredients, and the mixing may be completed in the truck mixer.  
17 Use the number of mixing revolutions in the truck mixer as specified for transit  
18 mixed concrete or reduce as indicated by mixer performance tests.

19 **(B) Mixing Time for Central Mixed Concrete**

20 Mixing time begins when all solid materials are in the mixing compartment and ends  
21 when any part of the concrete begins to discharge. In charging the mixer, water will enter  
22 in advance of cement and aggregate. Ensure all the water is substantially in the drum  
23 before 1/3 of the specified mixing time has elapsed. Count transfer time in multiple drum  
24 mixers as part of the mixing time.

25 Where mixer performance tests are not made, use a minimum mixing time of 90 seconds,  
26 providing that blending of materials during charging is achieved to the satisfaction of the  
27 Engineer. The minimum mixing time for an individual mixer is that which, as shown by  
28 mixer performance tests, will produce concrete in accordance with Table 1000-5, except  
29 that the mixing time shall not be less than 50 seconds under any circumstances.  
30 Maximum mixing time excluding discharge time is 150 seconds.

31 Sampling and testing for mixer performance tests will be done as provided below.  
32 Charge the mixer to its rated capacity with the materials and proportions to be used in the  
33 work and mixed at the recommended mixing speed to the target time. Stop mixing and  
34 begin discharging. Two samples of sufficient size to make the required tests will be  
35 taken after discharge of approximately 15% and 85% of the load.

<b>Property</b>	<b>Requirement</b>	<b>Test Method</b>
Difference in Test Samples Air Content, percent by volume of concrete	1.0%	AASHTO T 152
Slump	1.0"	AASHTO T 119
Coarse aggregate content, portion by weight of each sample retained on the No. 4 sieve	6.0%	AASHTO M 157
Weight	1.0 lb	AASHTO T 121
Average Compressive Strength at 7 days, percent of average	10.0% <sup>A</sup>	AASHTO T 22 AASHTO T 23

36 **A.** Tentative approval may be granted pending 7 day compressive strength tests.

## Section 1000

1 Each of the two samples of concrete will be separately tested for the properties listed in  
2 Table 1000-5. Tests will be conducted in accordance with the test procedures specified  
3 in Table 1000-5 or procedures established by the Materials and Tests Unit.

4 The mixer performance test described above will be performed on at least two batches of  
5 concrete. For the performance test to be acceptable, have all tests in each batch tested  
6 meet the requirements listed above.

7 The Engineer may recheck mixer performance at any time when, in his opinion,  
8 satisfactory mixing is not being accomplished.

9 Where satisfactory mixing cannot be accomplished in 90 seconds, the Engineer may  
10 increase the mixing time or require that the mixer be repaired or replaced before any  
11 further mixing can be done.

### 12 (C) Truck Mixers and Truck Agitators

13 When a truck mixer is used for complete mixing, mix each batch of concrete for at least  
14 70 revolutions of the drum or blades at the rate of rotation designated by the  
15 manufacturer of the equipment as mixing speed, unless otherwise directed by the  
16 Engineer. Unless the mixer is equipped with a counter which will distinguish between  
17 mixing and agitating speeds, perform the minimum required number of revolutions of the  
18 drum at mixing speed as directed, either at the batching plant before the mixer leaves  
19 for the work site and/or at the work site before the concrete is discharged.  
20 Perform any additional mixing at the speed designated by the manufacturer of the  
21 equipment as agitating speed. Put all materials including mixing water in the drum  
22 before actuating the revolution counter for determining the number of revolutions of the  
23 drum.

24 When a truck mixer or truck agitator is used to transport concrete that has been  
25 completely mixed in a stationary mixer, perform mixing during transport at agitating  
26 speed.

27 Provide concrete, when discharged from truck mixers or truck agitators, of the  
28 consistency and workability required for the work. Control the rate of discharge of the  
29 plastic concrete from the mixer drum by the speed or rotation of the drum in the  
30 discharge direction with the discharge gate fully open. If additional mixing water is  
31 necessary to produce the slump necessary for proper placement, add it only with  
32 permission and rotate the truck mixer drum at least 25 revolutions at mixing speed before  
33 discharge of any concrete. Additional mixing water will be allowed only if the maximum  
34 specified water content per cubic yard is not exceeded.

### 35 (D) Delivery

36 Use a ticket system for recording the transportation of batches from the proportioning  
37 plant to the site of the work. Use tickets furnished by the Engineer and fill it out in  
38 accordance with instructions issued by the Engineer. Issue the tickets to the truck  
39 operator at the proportioning plant for each load and have them signed by the plant  
40 inspector, which will signify that the concrete in the truck has been inspected before  
41 departure. Ensure each ticket shows the time batching was completed and if transit  
42 mixed, the number of revolutions at mixing speed, if any, at the plant. Deliver the tickets  
43 to the inspector at the site of the work. Do not use loads which do not carry such tickets  
44 and loads which do not arrive in satisfactory condition within the time limits specified in  
45 the work.

### 46 1000-12 VOLUMETRIC MIXED CONCRETE

47 Upon written request by the contractor, the Department may approve the use of concrete  
48 proportioned by volume. The volumetric producer must submit and have approved a process  
49 control plan and product quality control plan by the Materials and Tests Unit. If concrete is  
50 proportioned by volume, the other requirements of these specifications with the following

1 modifications will apply. Unless otherwise approved by the Department, use of concrete  
2 proportioned by volume shall be limited to Class B concrete and no more than 30 cy per unit  
3 per day.

#### 4 **(A) Materials**

5 Use materials that meet the requirements for the respective items except that they will be  
6 measured by a calibrated volume-weight relationship.

7 Storage facilities for all material shall be designed to permit the Department to make  
8 necessary inspections before the batching operations. The facilities shall permit  
9 identification of approved material at all times and shall be designed to avoid mixing  
10 with, or contaminating by, unapproved material. Coarse and fine aggregate shall be  
11 furnished and handled so variations in the moisture content affecting the uniform  
12 consistency of the concrete is avoided.

13 Moisture content of the coarse and fine aggregate will be made available onsite for the  
14 Engineer's review for each load. The frequency of moisture testing will be dependent on  
15 certain variables such as weather, season and source; however, moisture tests should be  
16 performed at least once at the beginning of the work day for each source material.  
17 Additional daily moisture tests for the coarse and fine aggregate shall be performed if  
18 requested by the Engineer.

19 Unused materials should be emptied from hopper daily. Concrete should not be mixed  
20 with materials left in the hopper overnight.

#### 21 **(B) Equipment**

22 Provide volumetric mixers with rating plates indicating that the performance of the mixer  
23 is in accordance with the Volumetric Mixer Manufacturer Bureau or equivalent. Mixers  
24 must comply with ASTM C685. Unless otherwise specified, all mixing operations must  
25 be in strict accordance with the manufacturer's recommended procedures. Such  
26 procedures shall be provided to the Department for review upon request.

27 The volumetric mixer shall be capable of carrying sufficient unmixed dry bulk cement,  
28 supplementary cementitious material (if required), fine aggregate, coarse aggregate,  
29 admixtures and water, in separate compartments and accurately proportioning the  
30 specified mix. Each batching or mixing unit (or both) shall carry in a prominent place a  
31 metal plate or plates on which are plainly marked the gross volume of the unit in terms of  
32 mixed concrete, discharge speed and the weight-calibrated constant of the machine in  
33 terms of a revolution counter or other output indicator.

34 The concrete mixing device shall be an auger-type continuous mixer used in conjunction  
35 with volumetric proportioning. The mixer shall produce concrete, uniform in color and  
36 appearance, with homogeneous distribution of the material throughout the mixture.  
37 Mixing time necessary to produce uniform concrete shall be established by the contractor  
38 and shall comply with other requirements of these specifications. Only equipment found  
39 acceptable in every respect and capable of producing uniform results will be permitted.

40 Each volumetric mixer shall be equipped with an onboard ticketing system that will  
41 electronically produce a record of all material used and their respective weights and the  
42 total volume of concrete placed. Alternate methods of recordation may be used if  
43 approved by the Engineer. Tickets shall identify at least the following information:

- 44 (1) Contractor Name
- 45 (2) Contractor Phone Number
- 46 (3) NCDOT Project No. and TIP No.
- 47 (4) Date
- 48 (5) Truck No.
- 49 (6) Ticket No.
- 50 (7) Time Start/End of Pour

**Section 1000**

- 1 (8) Mix ID and Description (Strength)
- 2 (9) Aggregate Moisture Before Mixing

3 **(C) Proportioning Devices**

4 Volume proportioning devices, such as counters, calibrated gate openings or flow meters,  
5 shall be easily accessible for controlling and determining the quantities of the ingredients  
6 discharged. All indicating devices that affect the accuracy of proportioning and mixing  
7 of concrete shall be in full view of and near enough to be read by the operator and  
8 Engineer while concrete is being produced. In operation, the entire measuring and  
9 dispensing mechanism shall produce the specified proportions of each ingredient.

10 Provide positive control of the flow of water and admixtures into the mixing chamber  
11 with a volumetric mixer. Indicate water flow by a flow meter and be readily adjustable to  
12 provide for slump control and/or minor variations in aggregate moisture. Provide a mixer  
13 capable of continuously circulating or mechanically agitating the admixtures.

14 Dispense liquid admixtures through a controlled, calibrated flow meter. A positive means  
15 to observe the continuous flow of material shall be provided. If an admixture requires  
16 diluting, the admixture shall be diluted and thoroughly mixed before introducing the  
17 admixture into the dispenser. When admixtures are diluted, the ratio of dilution and the  
18 mixing shall be approved by and performed in the presence of the Department.

19 The volumetric mixer shall be capable of measurement of cement, supplementary  
20 cementitious material (if required), liquids and aggregate being introduced into the mix.

21 **(D) Calibration**

22 Volume-weight relationships will be based on calibration. The proportioning devices  
23 shall be calibrated by the contractor before the start of each NCDOT job and  
24 subsequently at intervals recommended by the equipment manufacturer. Calibrations  
25 will be performed in the presence of the Department and subject to approval from the  
26 Department. Calibration of the cement and aggregate proportioning devices shall be  
27 accomplished by weighing (determining the mass of) each component. Calibration of the  
28 admixture and water proportioning devices shall be accomplished by weight (mass) or  
29 volume. Tolerances in proportioning the individual components will be as follows:

<b>TABLE 1000-6 VOLUMETRIC MIXED CONCRETE CALIBRATION TOLERANCES</b>	
<b>Item</b>	<b>Tolerance</b>
Cement, Weight (Mass) percent	0 to +4
Fine Aggregate, Weight (Mass) percent	± 2
Coarse Aggregate, Weight (Mass) percent	± 2
Admixtures, Weight (Mass) or Volume percent	± 3
Water, Weight (Mass) or Volume percent	± 1

30 Each volumetric mixer must be accompanied at all times by completed calibration  
31 worksheets and they shall be made available to the Department upon request.

32 **(E) Verification of Yield**

33 Verification of the proportioning devices may be required at any time by the Department.  
34 Verification shall be accomplished by proportioning the rock and sand based on the  
35 cement meter count for each concrete mobile mixer. Once the count (revolutions) for  
36 94 lbs. of cement has been determined then delivery of the correct amount of rock and  
37 sand can be verified.

**(F) Uniformity**

When concrete is produced, have present during all batching operations a Certified Concrete Batch Technician. During batching and placement, the sole duty of this employee is to supervise the production and control of the concrete, perform moisture tests, adjust mix proportions of aggregates for free moisture, complete and sign approved delivery tickets and assure quality control of the batching.

Two samples of sufficient size to make the required tests will be taken after discharge of approximately 15% and 85% of the load. Each of the two samples of concrete will be separately tested for the properties listed in Table 1000-6. Tests will be conducted in accordance with the test procedures specified in Table 1000-6 or procedures established by the Materials and Tests Unit. The Engineer may recheck mixer performance at any time when, in his opinion, satisfactory mixing is not being accomplished.

**SECTION 1002****SHOTCRETE PRODUCTION AND DELIVERY****1002-1 DESCRIPTION**

This section addresses shotcrete to be used for temporary support of excavations and other applications in accordance with the contract. Produce shotcrete by either the dry-mix or wet-mix process composed of Portland cement, fine and/or coarse aggregates, water and at the Contractor's option, supplementary cementitious materials. Include chemical admixtures as required or needed for shotcrete produced by the wet-mix process. Ground granulated blast furnace slag, fly ash or silica fume may be substituted for a portion of the Portland cement. Type IL, IS, IP or IT blended cement may be used instead of Portland cement.

Mixes for all shotcrete shall be designed by a Certified Concrete Mix Design Technician or an engineer licensed by the State of North Carolina. Shotcrete shall be applied by a nozzelman certified as an ACI Shotcrete Nozzelman in accordance with *ACI Certification Publication CP-60*. Nozzlemen shall be certified in either dry-mix or wet-mix shotcrete based on the process to be used for the work.

**1002-2 MATERIALS**

Refer to Division 10.

<b>Item</b>	<b>Section</b>
Chemical Admixtures	1024-3
Coarse Aggregate	1014-2
Fine Aggregate	1014-1
Fly Ash	1024-5
Ground Granulated Blast Furnace Slag	1024-6
Portland Cement	1024-1
Silica Fume	1024-7
Type IL Blended Cement	1024-1
Type IP Blended Cement	1024-1
Type IS Blended Cement	1024-1
Type IT Blended Cement	1024-1
Water	1024-4

**1002-3 SHOTCRETE FOR TEMPORARY SUPPORT OF EXCAVATIONS****(A) Composition and Design**

Submit proposed shotcrete mix designs for each shotcrete mix to be used in the work. Mix proportions shall be determined by a testing laboratory approved by the Department. Submit shotcrete mix designs in terms of saturated surface dry weights on Materials and Tests Form 312U at least 35 days before proposed use. Adjust batch proportions to compensate for surface moisture contained in the aggregates at the time of batching.